

# APPROVAL SHEET

## MULTILAYER CERAMIC CAPACITORS

Microwave Series (RF)

0201 to 0805 Sizes (6.3V to 500V)

NP0 Dielectric

RoHS Compliance

\*Contents in this sheet are subject to change without prior notice.

## 1. INTRODUCTION

MLCC consists of a conducting material and electrodes. To manufacture a chip-type SMT and achieve miniaturization, high density and high efficiency, ceramic condensers are used.

WTC RF series MLCC is used at high frequencies generally have a small temperature coefficient of capacitance, typical within the  $\pm 30\text{ppm}/^\circ\text{C}$  required for NP0 (COG) classification and have excellent conductivity internal electrode. Thus, WTC RF series MLCC will be with the feature of low ESR and high Q characteristics.

## 2. FEATURES

- High Q and low ESR performance at high frequency.
- Ultra low capacitance to 0.1pF.
- Can offer high precision tolerance to  $\pm 0.05\text{pF}$ .
- Quality improvement of telephone calls for low power loss and better performance.

## 3. APPLICATIONS

- Telecommunication products & equipments: Mobile phone, WLAN, Base station.
- RF module: Power amplifier, VCO.
- Tuners.


## 4. HOW TO ORDER

<u>RF</u>	<u>15</u>	<u>N</u>	<u>100</u>	<u>J</u>	<u>500</u>	<u>C</u>	<u>I</u>
<u>Series</u>	<u>Size</u>	<u>Dielectric</u>	<u>Capacitance</u>	<u>Tolerance</u>	<u>Rated voltage</u>	<u>Termination</u>	<u>Packaging</u>
RF=Ultra High Q & Low ESR	03=0201 (0603) 15=0402 (1005) 18=0603 (1608) 21=0805 (2012)	N=NP0	Two significant digits followed by no. of zeros. And R is in place of decimal point.  eg.: 0R5=0.5pF 1R0=1.0pF 100=10x10 <sup>0</sup> =10pF	A= $\pm 0.05\text{pF}$ B= $\pm 0.1\text{pF}$ C= $\pm 0.25\text{pF}$ D= $\pm 0.5\text{pF}$ F= $\pm 1\%$ G= $\pm 2\%$ J= $\pm 5\%$	Two significant digits followed by no. of zeros. And R is in place of decimal point.  6R3=6.3 VDC 100=10 VDC 250=25 VDC 500=50 VDC 101=100 VDC 251=250 VDC 501=500 VDC	C=Cu/Ni/Sn	T=7" reeled G= 13" reeled

## 5. EXTERNAL DIMENSIONS

Size Inch (mm)	L (mm)	W (mm)	T (mm)/Symbol	Remark	M <sub>B</sub> (mm)
0201 (0603)	0.60±0.03	0.30±0.03	0.30±0.03	L #	0.15±0.05
0402 (1005)	1.00±0.05	0.50±0.05	0.50±0.05	N #	0.25+0.05/-0.10
0603 (1608)	1.60±0.10	0.80±0.10	0.80±0.07	S	0.40±0.15
0805 (2012)	2.00±0.20	1.25±0.20	0.85±0.10	T	0.50±0.20

# Reflow soldering only is recommended.



## 6. GENERAL ELECTRICAL DATA

Dielectric	NP0
Size	0201, 0402, 0603, 0805
Capacitance*	0201: 0.1pF to 33pF; 0402: 0.1pF to 100pF; 0603: 0.3pF to 47pF; 0805: 0.3pF to 100pF
Capacitance tolerance	Cap≤5pF: A (±0.05pF), B (±0.1pF), C (±0.25pF) 5pF<Cap<10pF: B (±0.1pF), C (±0.25pF), D (±0.5pF) Cap≥10pF: F (±1%), G (±2%), J (±5%)
Rated voltage (WVDC)	6.3V, 10V, 25V, 50V, 100V, 250V, 500V
Q*	Cap≥30pF, Q≥1000; Cap<30pF, Q≥400+20C
Insulation resistance at U <sub>r</sub>	≥10GΩ or R <sub>x</sub> C≥100Ω·F whichever is smaller.
Operating temperature	-55 to +125°C
Capacitance change	±30ppm/°C; 0201Cap≥22pF, ±60ppm/°C
Termination	Ni/Sn (lead-free termination)

\* Measured at the conditions of 25°C ambient temperature and 30~70% related humidity.

Apply 1.0±0.2Vrms, 1.0MHz±10% for Cap≤1000pF and 1.0±0.2Vrms, 1.0kHz±10% for Cap>1000pF.

## 7. PACKAGING DIMENSION AND QUANTITY

Size	Thickness (mm)/Symbol		Paper tape	
			7" reel	13" reel
0201 (0603)	0.30±0.03	L	15k	70k
0402 (1005)	0.50±0.05	N	10k	50k
0603 (1608)	0.80±0.07	S	4k	15k
0805 (2012)	0.85±0.10	T	4k	15k

Unit: pieces

## 8. CAPACITANCE RANGE

DIELECTRIC		NP0							Tolerance
SIZE		0201				0402			
RATED VOLTAGE (VDC)		6.3	10	25	50	25	50	100	
Capacitance	0.1pF (0R1)	L	L	L	L	N	N	N	B
	0.2pF (0R2)	L	L	L	L	N	N	N	A, B
	0.3pF (0R3)	L	L	L	L	N	N	N	A, B
	0.4pF (0R4)	L	L	L	L	N	N	N	A, B
	0.5pF (0R5)	L	L	L	L	N	N	N	A, B, C
	0.6pF (0R6)	L	L	L	L	N	N	N	A, B, C
	0.7pF (0R7)	L	L	L	L	N	N	N	A, B, C
	0.8pF (0R8)	L	L	L	L	N	N	N	A, B, C
	0.9pF (0R9)	L	L	L	L	N	N	N	A, B, C
	1.0pF (1R0)	L	L	L	L	N	N	N	A, B, C
	1.1pF (1R1)	L	L	L	L	N	N	N	A, B, C
	1.2pF (1R2)	L	L	L	L	N	N	N	A, B, C
	1.3pF (1R3)	L	L	L	L	N	N	N	A, B, C
	1.4pF (1R4)	L	L	L	L	N	N	N	A, B, C
	1.5pF (1R5)	L	L	L	L	N	N	N	A, B, C
	1.6pF (1R6)	L	L	L	L	N	N	N	A, B, C
	1.7pF (1R7)	L	L	L	L	N	N	N	A, B, C
	1.8pF (1R8)	L	L	L	L	N	N	N	A, B, C
	1.9pF (1R9)	L	L	L	L	N	N	N	A, B, C
	2.0pF (2R0)	L	L	L	L	N	N	N	A, B, C
	2.1pF (2R1)	L	L	L	L	N	N	N	A, B, C
	2.2pF (2R2)	L	L	L	L	N	N	N	A, B, C
	2.3pF (2R3)	L	L	L	L	N	N	N	A, B, C
	2.4pF (2R4)	L	L	L	L	N	N	N	A, B, C
	2.5pF (2R5)	L	L	L	L	N	N	N	A, B, C
	2.6pF (2R6)	L	L	L	L	N	N	N	A, B, C
	2.7pF (2R7)	L	L	L	L	N	N	N	A, B, C
	2.8pF (2R8)	L	L	L	L	N	N	N	A, B, C
	2.9pF (2R9)	L	L	L	L	N	N	N	A, B, C
	3.0pF (3R0)	L	L	L	L	N	N	N	A, B, C
	3.1pF (3R1)	L	L	L	L	N	N	N	A, B, C
	3.2pF (3R2)	L	L	L	L	N	N	N	A, B, C
	3.3pF (3R3)	L	L	L	L	N	N	N	A, B, C
	3.4pF (3R4)	L	L	L	L	N	N	N	A, B, C
	3.5pF (3R5)	L	L	L	L	N	N	N	A, B, C
	3.6pF (3R6)	L	L	L	L	N	N	N	A, B, C
	3.7pF (3R7)	L	L	L	L	N	N	N	A, B, C
	3.8pF (3R8)	L	L	L	L	N	N	N	A, B, C
	3.9pF (3R9)	L	L	L	L	N	N	N	A, B, C
	4.0pF (4R0)	L	L	L	L	N	N	N	A, B, C
4.1pF (4R1)	L	L	L	L	N	N	N	A, B, C	
4.2pF (4R2)	L	L	L	L	N	N	N	A, B, C	
4.3pF (4R3)	L	L	L	L	N	N	N	A, B, C	
4.4pF (4R4)	L	L	L	L	N	N	N	A, B, C	
4.5pF (4R5)	L	L	L	L	N	N	N	A, B, C	
4.6pF (4R6)	L	L	L	L	N	N	N	A, B, C	
4.7pF (4R7)	L	L	L	L	N	N	N	A, B, C	
4.8pF (4R8)	L	L	L	L	N	N	N	A, B, C	
4.9pF (4R9)	L	L	L	L	N	N	N	A, B, C	
5.0pF (5R0)	L	L	L	L	N	N	N	A, B, C	
5.1pF (5R1)	L	L	L	L	N	N	N	B, C, D	
5.2pF (5R2)	L	L	L	L	N	N	N	B, C, D	
5.3pF (5R3)	L	L	L	L	N	N	N	B, C, D	
5.4pF (5R4)	L	L	L	L	N	N	N	B, C, D	
5.5pF (5R5)	L	L	L	L	N	N	N	B, C, D	
5.6pF (5R6)	L	L	L	L	N	N	N	B, C, D	
5.7pF (5R7)	L	L	L	L	N	N	N	B, C, D	
5.8pF (5R8)	L	L	L	L	N	N	N	B, C, D	
5.9pF (5R9)	L	L	L	L	N	N	N	B, C, D	
6.0pF (6R0)	L	L	L	L	N	N	N	B, C, D	

1. The letter in cell is expressed the symbol of product thickness.

2. For more information about products with special capacitance or other data, please contact WTC local representative.

DIELECTRIC		NP0							Tolerance
SIZE		0201				0402			
RATED VOLTAGE (VDC)		6.3	10	25	50	25	50	100	
Capacitance	6.1pF (6R1)	L	L	L	L	N	N	N	B, C, D
	6.2pF (6R2)	L	L	L	L	N	N	N	B, C, D
	6.3pF (6R3)	L	L	L	L	N	N	N	B, C, D
	6.4pF (6R4)	L	L	L	L	N	N	N	B, C, D
	6.5pF (6R5)	L	L	L	L	N	N	N	B, C, D
	6.6pF (6R6)	L	L	L	L	N	N	N	B, C, D
	6.7pF (6R7)	L	L	L	L	N	N	N	B, C, D
	6.8pF (6R8)	L	L	L	L	N	N	N	B, C, D
	6.9pF (6R9)	L	L	L	L	N	N	N	B, C, D
	7.0pF (7R0)	L	L	L	L	N	N	N	B, C, D
	7.1pF (7R1)	L	L	L	L	N	N	N	B, C, D
	7.2pF (7R2)	L	L	L	L	N	N	N	B, C, D
	7.3pF (7R3)	L	L	L	L	N	N	N	B, C, D
	7.4pF (7R4)	L	L	L	L	N	N	N	B, C, D
	7.5pF (7R5)	L	L	L	L	N	N	N	B, C, D
	7.6pF (7R6)	L	L	L	L	N	N	N	B, C, D
	7.7pF (7R7)	L	L	L	L	N	N	N	B, C, D
	7.8pF (7R8)	L	L	L	L	N	N	N	B, C, D
	7.9pF (7R9)	L	L	L	L	N	N	N	B, C, D
	8.0pF (8R0)	L	L	L	L	N	N	N	B, C, D
	8.1pF (8R1)	L	L	L	L	N	N	N	B, C, D
	8.2pF (8R2)	L	L	L	L	N	N	N	B, C, D
	8.3pF (8R3)	L	L	L	L	N	N	N	B, C, D
	8.4pF (8R4)	L	L	L	L	N	N	N	B, C, D
	8.5pF (8R5)	L	L	L	L	N	N	N	B, C, D
	8.6pF (8R6)	L	L	L	L	N	N	N	B, C, D
	8.7pF (8R7)	L	L	L	L	N	N	N	B, C, D
	8.8pF (8R8)	L	L	L	L	N	N	N	B, C, D
	8.9pF (8R9)	L	L	L	L	N	N	N	B, C, D
	9.0pF (9R0)	L	L	L	L	N	N	N	B, C, D
	9.1pF (9R1)	L	L	L	L	N	N	N	B, C, D
	9.2pF (9R2)	L	L	L	L	N	N	N	B, C, D
	9.3pF (9R3)	L	L	L	L	N	N	N	B, C, D
	9.4pF (9R4)	L	L	L	L	N	N	N	B, C, D
	9.5pF (9R5)	L	L	L	L	N	N	N	B, C, D
	9.6pF (9R6)	L	L	L	L	N	N	N	B, C, D
	9.7pF (9R7)	L	L	L	L	N	N	N	B, C, D
	9.8pF (9R8)	L	L	L	L	N	N	N	B, C, D
	9.9pF (9R9)	L	L	L	L	N	N	N	B, C, D
	10pF (100)	L	L	L	L	N	N	N	F, G, J
11pF (110)	L	L	L	L	N	N	N	F, G, J	
12pF (120)	L	L	L	L	N	N	N	F, G, J	
13pF (130)	L	L	L	L	N	N	N	F, G, J	
15pF (150)	L	L	L	L	N	N	N	F, G, J	
16pF (160)	L	L	L	L	N	N	N	F, G, J	
18pF (180)	L	L	L	L	N	N	N	F, G, J	
20pF (200)	L	L	L	L	N	N	N	F, G, J	
22pF (220)	L	L	L	L	N	N	N	F, G, J	
24pF (240)	L	L	L	L	N	N	N	F, G, J	
27pF (270)	L	L	L	L	N	N	N	F, G, J	
30pF (300)	L	L	L	L	N	N	N	F, G, J	
33pF (330)	L	L	L	L	N	N	N	F, G, J	
36pF (360)					N	N	N	F, G, J	
39pF (390)					N	N	N	F, G, J	
43pF (430)					N	N	N	F, G, J	
47pF (470)					N	N	N	F, G, J	
56pF (560)					N	N	N	F, G, J	
68pF (680)					N			F, G, J	
82pF (820)					N			F, G, J	
100pF (101)					N			F, G, J	

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.




DIELECTRIC		NP0							Tolerance
SIZE		0603			0805				
RATED VOLTAGE (VDC)		50	100	250	50	100	250	500	
Capacitance	0.1pF (0R1)								
	0.2pF (0R2)								
	0.3pF (0R3)	S	S	S	T	T	T	T	A, B
	0.4pF (0R4)	S	S	S	T	T	T	T	A, B
	0.5pF (0R5)	S	S	S	T	T	T	T	A, B, C
	0.6pF (0R6)	S	S	S	T	T	T	T	A, B, C
	0.7pF (0R7)	S	S	S	T	T	T	T	A, B, C
	0.8pF (0R8)	S	S	S	T	T	T	T	A, B, C
	0.9pF (0R9)	S	S	S	T	T	T	T	A, B, C
	1.0pF (1R0)	S	S	S	T	T	T	T	A, B, C
	1.1pF (1R1)	S	S	S	T	T	T	T	A, B, C
	1.2pF (1R2)	S	S	S	T	T	T	T	A, B, C
	1.3pF (1R3)	S	S	S	T	T	T	T	A, B, C
	1.4pF (1R4)	S	S	S	T	T	T	T	A, B, C
	1.5pF (1R5)	S	S	S	T	T	T	T	A, B, C
	1.6pF (1R6)	S	S	S	T	T	T	T	A, B, C
	1.7pF (1R7)	S	S	S	T	T	T	T	A, B, C
	1.8pF (1R8)	S	S	S	T	T	T	T	A, B, C
	1.9pF (1R9)	S	S	S	T	T	T	T	A, B, C
	2.0pF (2R0)	S	S	S	T	T	T	T	A, B, C
	2.1pF (2R1)	S	S	S	T	T	T	T	A, B, C
	2.2pF (2R2)	S	S	S	T	T	T	T	A, B, C
	2.3pF (2R3)	S	S	S	T	T	T	T	A, B, C
	2.4pF (2R4)	S	S	S	T	T	T	T	A, B, C
	2.5pF (2R5)	S	S	S	T	T	T	T	A, B, C
	2.6pF (2R6)	S	S	S	T	T	T	T	A, B, C
	2.7pF (2R7)	S	S	S	T	T	T	T	A, B, C
	2.8pF (2R8)	S	S	S	T	T	T	T	A, B, C
	2.9pF (2R9)	S	S	S	T	T	T	T	A, B, C
	3.0pF (3R0)	S	S	S	T	T	T	T	A, B, C
	3.1pF (3R1)	S	S	S	T	T	T	T	A, B, C
	3.2pF (3R2)	S	S	S	T	T	T	T	A, B, C
	3.3pF (3R3)	S	S	S	T	T	T	T	A, B, C
	3.4pF (3R4)	S	S	S	T	T	T	T	A, B, C
	3.5pF (3R5)	S	S	S	T	T	T	T	A, B, C
	3.6pF (3R6)	S	S	S	T	T	T	T	A, B, C
	3.7pF (3R7)	S	S	S	T	T	T	T	A, B, C
	3.8pF (3R8)	S	S	S	T	T	T	T	A, B, C
	3.9pF (3R9)	S	S	S	T	T	T	T	A, B, C
	4.0pF (4R0)	S	S	S	T	T	T	T	A, B, C
4.1pF (4R1)	S	S	S	T	T	T	T	A, B, C	
4.2pF (4R2)	S	S	S	T	T	T	T	A, B, C	
4.3pF (4R3)	S	S	S	T	T	T	T	A, B, C	
4.4pF (4R4)	S	S	S	T	T	T	T	A, B, C	
4.5pF (4R5)	S	S	S	T	T	T	T	A, B, C	
4.6pF (4R6)	S	S	S	T	T	T	T	A, B, C	
4.7pF (4R7)	S	S	S	T	T	T	T	A, B, C	
4.8pF (4R8)	S	S	S	T	T	T	T	A, B, C	
4.9pF (4R9)	S	S	S	T	T	T	T	A, B, C	
5.0pF (5R0)	S	S	S	T	T	T	T	A, B, C	
5.1pF (5R1)	S	S	S	T	T	T	T	B, C, D	
5.2pF (5R2)	S	S	S	T	T	T	T	B, C, D	
5.3pF (5R3)	S	S	S	T	T	T	T	B, C, D	
5.4pF (5R4)	S	S	S	T	T	T	T	B, C, D	
5.5pF (5R5)	S	S	S	T	T	T	T	B, C, D	
5.6pF (5R6)	S	S	S	T	T	T	T	B, C, D	
5.7pF (5R7)	S	S	S	T	T	T	T	B, C, D	
5.8pF (5R8)	S	S	S	T	T	T	T	B, C, D	
5.9pF (5R9)	S	S	S	T	T	T	T	B, C, D	
6.0pF (6R0)	S	S	S	T	T	T	T	B, C, D	

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

DIELECTRIC		NP0							Tolerance
SIZE		0603			0805				
RATED VOLTAGE (VDC)		50	100	250	50	100	250	500	
Capacitance	6.1pF (6R1)	S	S	S	T	T	T	T	B, C, D
	6.2pF (6R2)	S	S	S	T	T	T	T	B, C, D
	6.3pF (6R3)	S	S	S	T	T	T	T	B, C, D
	6.4pF (6R4)	S	S	S	T	T	T	T	B, C, D
	6.5pF (6R5)	S	S	S	T	T	T	T	B, C, D
	6.6pF (6R6)	S	S	S	T	T	T	T	B, C, D
	6.7pF (6R7)	S	S	S	T	T	T	T	B, C, D
	6.8pF (6R8)	S	S	S	T	T	T	T	B, C, D
	6.9pF (6R9)	S	S	S	T	T	T	T	B, C, D
	7.0pF (7R0)	S	S	S	T	T	T	T	B, C, D
	7.1pF (7R1)	S	S	S	T	T	T	T	B, C, D
	7.2pF (7R2)	S	S	S	T	T	T	T	B, C, D
	7.3pF (7R3)	S	S	S	T	T	T	T	B, C, D
	7.4pF (7R4)	S	S	S	T	T	T	T	B, C, D
	7.5pF (7R5)	S	S	S	T	T	T	T	B, C, D
	7.6pF (7R6)	S	S	S	T	T	T	T	B, C, D
	7.7pF (7R7)	S	S	S	T	T	T	T	B, C, D
	7.8pF (7R8)	S	S	S	T	T	T	T	B, C, D
	7.9pF (7R9)	S	S	S	T	T	T	T	B, C, D
	8.0pF (8R0)	S	S	S	T	T	T	T	B, C, D
	8.1pF (8R1)	S	S	S	T	T	T	T	B, C, D
	8.2pF (8R2)	S	S	S	T	T	T	T	B, C, D
	8.3pF (8R3)	S	S	S	T	T	T	T	B, C, D
	8.4pF (8R4)	S	S	S	T	T	T	T	B, C, D
	8.5pF (8R5)	S	S	S	T	T	T	T	B, C, D
	8.6pF (8R6)	S	S	S	T	T	T	T	B, C, D
	8.7pF (8R7)	S	S	S	T	T	T	T	B, C, D
	8.8pF (8R8)	S	S	S	T	T	T	T	B, C, D
	8.9pF (8R9)	S	S	S	T	T	T	T	B, C, D
	9.0pF (9R0)	S	S	S	T	T	T	T	B, C, D
	9.1pF (9R1)	S	S	S	T	T	T	T	B, C, D
	9.2pF (9R2)	S	S	S	T	T	T	T	B, C, D
	9.3pF (9R3)	S	S	S	T	T	T	T	B, C, D
	9.4pF (9R4)	S	S	S	T	T	T	T	B, C, D
	9.5pF (9R5)	S	S	S	T	T	T	T	B, C, D
	9.6pF (9R6)	S	S	S	T	T	T	T	B, C, D
	9.7pF (9R7)	S	S	S	T	T	T	T	B, C, D
	9.8pF (9R8)	S	S	S	T	T	T	T	B, C, D
	9.9pF (9R9)	S	S	S	T	T	T	T	B, C, D
	10pF (100)	S	S	S	T	T	T	T	F, G, J
11pF (110)	S	S	S	T	T	T	T	F, G, J	
12pF (120)	S	S	S	T	T	T	T	F, G, J	
13pF (130)	S	S	S	T	T	T	T	F, G, J	
15pF (150)	S	S	S	T	T	T	T	F, G, J	
16pF (160)	S	S	S	T	T	T	T	F, G, J	
18pF (180)	S	S	S	T	T	T	T	F, G, J	
20pF (200)	S	S	S	T	T	T	T	F, G, J	
22pF (220)	S	S	S	T	T	T	T	F, G, J	
24pF (240)	S	S	S	T	T	T	T	F, G, J	
27pF (270)	S	S	S	T	T	T	T	F, G, J	
30pF (300)	S	S	S	T	T	T	T	F, G, J	
33pF (330)	S	S	S	T	T	T	T	F, G, J	
36pF (360)	S	S	S	T	T	T	T	F, G, J	
39pF (390)	S	S	S	T	T	T	T	F, G, J	
43pF (430)	S	S	S	T	T	T	T	F, G, J	
47pF (470)	S	S	S	T	T	T	T	F, G, J	
56pF (560)	S	S	S	T	T	T	T	F, G, J	
68pF (680)	S	S	S	T	T	T	T	F, G, J	
82pF (820)	S	S	S	T	T	T	T	F, G, J	
100pF (101)	S	S	S	T	T	T	T	F, G, J	

1. The letter in cell is expressed the symbol of product thickness.
2. For more information about products with special capacitance or other data, please contact WTC local representative.

## 9. ELECTRICAL CHARACTERISTICS








Fig. 5 Self resonance frequency vs. Capacitance (0201 size)




Fig. 6 Self resonance frequency vs. Capacitance (0402 size)




Fig. 7 S<sub>11</sub> vs. frequency. (0201 size)




Fig. 8 S<sub>11</sub> vs. frequency. (0402 size)




Fig. 9 S<sub>21</sub> vs. frequency. (0201 size)




Fig. 10 S<sub>21</sub> vs. frequency. (0402 size)

## 10. RELIABILITY TEST CONDITIONS AND REQUIREMENTS

No.	Item	Test Conditions	Requirements
1.	Visual and Mechanical	---	No remarkable defect. Dimensions to conform to individual specification sheet.
2.	Capacitance	1.0±0.2Vrms, 1MHz±10%	Shall not exceed the limits given in the detailed spec.
3.	Q/ D.F. (Dissipation Factor)	At 25°C ambient temperature.	Cap≥30pF, Q≥1000; Cap<30pF, Q≥400+20C
4.	Dielectric Strength	<ul style="list-style-type: none"> <li>* To apply voltage: ≤100V, ≥250% of rated voltage.</li> <li>* Duration: 1 to 5 sec.</li> <li>* Charge and discharge current less than 50mA.</li> <li>* To apply voltage:</li> <li>200V~300V            ≥2 times VDC</li> <li>500V~999V          ≥1.5 times VDC</li> <li>1000V~3000V        ≥1.2 times VDC</li> <li>* Cut-off, set at 10mA</li> <li>* TEST= 15 sec.</li> <li>* RAMP=0</li> </ul>	No evidence of damage or flash over during test.
5.	Insulation Resistance	<ul style="list-style-type: none"> <li>≤100V : To apply rated voltage for max. 120 sec.</li> <li>≥200V : To apply rated voltage (500V max.) for 60 sec.</li> </ul>	≥10GΩ or RxC≥100Ω-F whichever is smaller
6.	Temperature Coefficient	<ul style="list-style-type: none"> <li>* With no electrical load.</li> <li>* Operating temperature: -55~125°C at 25°C</li> </ul>	<ul style="list-style-type: none"> <li>* Capacitance change: within ±30ppm/°C;</li> <li>0201Cap≥22pF, within ±60ppm/°C</li> </ul>
7.	Adhesive Strength of Termination	<ul style="list-style-type: none"> <li>* Pressurizing force :</li> <li>0201: 2N</li> <li>0402 &amp; 0603: 5N</li> <li>&gt;0603: 10N</li> <li>* Test time: 10±1 sec.</li> </ul>	No remarkable damage or removal of the terminations.
8.	Vibration Resistance	<ul style="list-style-type: none"> <li>* Vibration frequency: 10~55 Hz/min.</li> <li>* Total amplitude: 1.5mm</li> <li>* Test time: 6 hrs. (Two hrs each in three mutually perpendicular directions.)</li> <li>* Measurement to be made after keeping at room temp. for 24±2 hrs.</li> </ul>	<ul style="list-style-type: none"> <li>* No remarkable damage.</li> <li>* Cap change and Q/D.F.: To meet initial spec.</li> </ul>
9.	Solderability	<ul style="list-style-type: none"> <li>* Solder temperature: 235±5°C</li> <li>* Dipping time: 2±0.5 sec.</li> </ul>	95% min. coverage of all metalized area.
10.	Bending Test	<ul style="list-style-type: none"> <li>* The middle part of substrate shall be pressurized by means of the pressurizing rod at a rate of about 1 mm per second until the deflection becomes 1 mm and then the pressure shall be maintained for 5±1 sec.</li> <li>* Measurement to be made after keeping at room temp. for 24±2 hrs.</li> </ul>	<ul style="list-style-type: none"> <li>* No remarkable damage.</li> <li>* Cap change: within ±5.0% or ±0.5pF whichever is larger. (This capacitance change means the change of capacitance under specified flexure of substrate from the capacitance measured before the test.)</li> </ul>
11.	Resistance to Soldering Heat	<ul style="list-style-type: none"> <li>* Solder temperature: 260±5°C</li> <li>* Dipping time: 10±1 sec</li> <li>* Preheating: 120 to 150°C for 1 minute before immerse the capacitor in a eutectic solder.</li> <li>* Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp.</li> <li>* Measurement to be made after keeping at room temp. for 24±2 hrs.</li> </ul>	<ul style="list-style-type: none"> <li>* No remarkable damage.</li> <li>* Cap change: within ±2.5% or ±0.25pF whichever is larger.</li> <li>* Q/D.F., I.R. and dielectric strength: To meet initial requirements.</li> <li>* 25% max. leaching on each edge.</li> </ul>

No.	Item	Test Condition	Requirements																																
12.	Temperature Cycle	<p>* Conduct the five cycles according to the temperatures and time.</p> <table border="1"> <thead> <tr> <th>Step</th> <th>Temp. (°C)</th> <th>Time (min.)</th> </tr> </thead> <tbody> <tr> <td>1</td> <td>Min. operating temp. +0/-3</td> <td>30±3</td> </tr> <tr> <td>2</td> <td>Room temp.</td> <td>2~3</td> </tr> <tr> <td>3</td> <td>Max. operating temp. +3/-0</td> <td>30±3</td> </tr> <tr> <td>4</td> <td>Room temp.</td> <td>2~3</td> </tr> </tbody> </table> <p>* Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.</p>	Step	Temp. (°C)	Time (min.)	1	Min. operating temp. +0/-3	30±3	2	Room temp.	2~3	3	Max. operating temp. +3/-0	30±3	4	Room temp.	2~3	<p>No remarkable damage. Cap change : within ±2.5% or ±0.25pF whichever is larger. * Q/D.F., I.R. and dielectric strength: To meet initial requirements.</p>																	
Step	Temp. (°C)	Time (min.)																																	
1	Min. operating temp. +0/-3	30±3																																	
2	Room temp.	2~3																																	
3	Max. operating temp. +3/-0	30±3																																	
4	Room temp.	2~3																																	
13.	Humidity (Damp Heat) Steady State	<p>* Test temp.: 40±2°C * Humidity: 90~95% RH * Test time: 500+24/-0hrs. * Before initial measurement (Class II only): Perform 150+0/-10°C for 1 hr and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.</p>	<p>* No remarkable damage. * Cap change: within ±5.0% or ±0.5pF whichever is larger. * Q/D.F. value: Cap≥30pF, Q≥350; 10pF≤Cap&lt;30pF, Q≥275+2.5C Cap&lt;10pF, Q≥200+10C * I.R.: ≥1GΩ.</p>																																
14.	Humidity (Damp Heat) Load	<p>* Test temp.: 40±2°C * Humidity: 90~95%RH * Test time: 500+24/-0 hrs. * To apply voltage : rated voltage * Before initial measurement (Class II only): To apply test voltage for 1hr at 40°C and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs.</p>	<p>* No remarkable damage. * Cap change: within ±7.5% or ±0.75pF whichever is larger. * Q/D.F. value: Cap≥30pF, Q≥200; Cap&lt;30pF, Q≥100+10/3C * I.R.: ≥500MΩ.</p>																																
15.	High Temperature Load (Endurance)	<p>* Test temp.: 125±3°C * To apply voltage: (1) 10V ≤ Ur &lt; 500V: 200% of rated voltage. (2) ≤ 6.3V or 500V: 150% of rated voltage. (3) Ur ≥ 630V: 120% of rated voltage. * Test time: 1000+24/-0 hrs. * Before initial measurement (Class II only): To apply test voltage for 1hr at test temp. and then set for 24±2 hrs at room temp. * Measurement to be made after keeping at room temp. for 24±2 hrs</p>	<p>* No remarkable damage. * Cap change: within ±3.0% or ±0.3pF whichever is larger. * Q/D.F. value: Cap≥30pF, Q≥350 10pF≤Cap&lt;30pF, Q≥275+2.5C Cap&lt;10pF, Q≥200+10C * I.R.: ≥1GΩ.</p>																																
16.	ESR	<p>The ESR should be measured at room temperature and tested at frequency 1±0.1 GHz.</p> <table border="1"> <thead> <tr> <th colspan="2">0201</th> <th colspan="2">0402</th> </tr> </thead> <tbody> <tr> <td colspan="2">0.1pF≤Cap≤1pF:&lt; 350mΩ</td> <td colspan="2">0.1pF≤Cap≤1pF:&lt; 350mΩ</td> </tr> <tr> <td colspan="2">1pF&lt;Cap≤5pF:&lt; 300mΩ</td> <td colspan="2">1pF&lt;Cap≤5pF:&lt; 300mΩ</td> </tr> <tr> <td colspan="2">5pF&lt;Cap≤22pF:&lt; 250mΩ</td> <td colspan="2">5pF&lt;Cap≤100pF:&lt; 250mΩ</td> </tr> </tbody> </table> <table border="1"> <thead> <tr> <th colspan="2">0603</th> <th colspan="2">0805</th> </tr> </thead> <tbody> <tr> <td colspan="2">0.3pF≤Cap≤1pF:&lt; 1500mΩ</td> <td colspan="2">0.3pF≤Cap≤1pF: &lt; 1500mΩ</td> </tr> <tr> <td colspan="2">1pF&lt;Cap≤10pF:&lt; 250mΩ</td> <td colspan="2">1pF&lt;Cap≤10pF: &lt; 250mΩ</td> </tr> <tr> <td colspan="2">10pF&lt;Cap≤100pF:&lt; 200mΩ</td> <td colspan="2">Cap&gt;10pF: &lt; 200mΩ</td> </tr> </tbody> </table> <p>The ESR should be measured at room temperature and tested at frequency 500±50 MHz.</p>	0201		0402		0.1pF≤Cap≤1pF:< 350mΩ		0.1pF≤Cap≤1pF:< 350mΩ		1pF<Cap≤5pF:< 300mΩ		1pF<Cap≤5pF:< 300mΩ		5pF<Cap≤22pF:< 250mΩ		5pF<Cap≤100pF:< 250mΩ		0603		0805		0.3pF≤Cap≤1pF:< 1500mΩ		0.3pF≤Cap≤1pF: < 1500mΩ		1pF<Cap≤10pF:< 250mΩ		1pF<Cap≤10pF: < 250mΩ		10pF<Cap≤100pF:< 200mΩ		Cap>10pF: < 200mΩ		<p>0201, 22pF≤Cap≤33pF: &lt; 300mΩ</p>
0201		0402																																	
0.1pF≤Cap≤1pF:< 350mΩ		0.1pF≤Cap≤1pF:< 350mΩ																																	
1pF<Cap≤5pF:< 300mΩ		1pF<Cap≤5pF:< 300mΩ																																	
5pF<Cap≤22pF:< 250mΩ		5pF<Cap≤100pF:< 250mΩ																																	
0603		0805																																	
0.3pF≤Cap≤1pF:< 1500mΩ		0.3pF≤Cap≤1pF: < 1500mΩ																																	
1pF<Cap≤10pF:< 250mΩ		1pF<Cap≤10pF: < 250mΩ																																	
10pF<Cap≤100pF:< 200mΩ		Cap>10pF: < 200mΩ																																	

## APPENDIXES

### ▣ Tape & reel dimensions




Fig. 11 The dimension of paper tape





Fig. 12 The dimension of reel

Size	0201	0402	0603	0805
Thickness	L	N	S	T
A <sub>0</sub>	0.37±0.03	0.62±0.05	1.00 +0.05/-0.1	1.50±0.10
B <sub>0</sub>	0.67±0.03	1.12±0.05	1.80±0.10	2.30±0.10
T	0.42±0.03	0.60±0.05	0.95±0.05	0.95±0.05
K <sub>0</sub>	-	-	-	-
W	8.00±0.10	8.00±0.10	8.00±0.10	8.00±0.10
P <sub>0</sub>	4.00±0.10	4.00±0.10	4.00±0.10	4.00±0.10
10xP <sub>0</sub>	40.0±0.10	40.0±0.10	40.0±0.20	40.0±0.20
P <sub>1</sub>	2.00±0.05	2.00±0.05	4.00±0.10	4.00±0.10
P <sub>2</sub>	2.00±0.05	2.00±0.05	2.00±0.05	2.00±0.05
D <sub>0</sub>	1.55±0.05	1.55±0.05	1.55±0.05	1.55±0.05
D <sub>1</sub>	-	-	-	-
E	1.75±0.05	1.75±0.05	1.75±0.05	1.75±0.05
F	3.50±0.05	3.50±0.05	3.50±0.05	3.50±0.05

Size	0201, 0402, 0603, 0805	
Reel size	7"	13"
C	13.0+0.5/-0.2	13.0+0.5/-0.2
W <sub>1</sub>	8.4+1.5/-0	8.4+1.5/-0
A	178.0±1.0	330.0±1.0
N	60.0+1.0/-0	100±1.0

### ▣ Description of customer label



- a. Customer name
- b. WTC order series and item number
- c. Customer P/O
- d. Customer P/N
- e. Description of product
- f. Quantity
- g. Bar code including quantity & WTC P/N or customer
- h. WTC P/N
- i. Shipping date
- j. Order bar code including series and item numbers
- k. Serial number of label

### ▣ Constructions

No.	Name	NP0
①	Ceramic material	BaTiO <sub>3</sub> based
②	Inner electrode	Cu
③	Termination	Inner layer
④		Middle layer
⑤		Outer layer
		Sn (Matt)




Fig. 13 The construction of MLCC

▣ **Storage and handling conditions**

- (1) To store products at 5 to 40°C ambient temperature and 20 to 70% related humidity conditions.
- (2) The product is recommended to be used within one year after shipment. Check solderability in case of shelf life extension is needed.

Cautions:

- a. The corrosive gas reacts on the terminal electrodes of capacitors, and results in the poor solderability. Do not store the capacitors in the ambience of corrosive gas (e.g., hydrogen sulfide, sulfur dioxide, chlorine, ammonia gas etc.)
- b. In corrosive atmosphere, solderability might be degraded, and silver migration might occur to cause low reliability.
- c. Due to the dewing by rapid humidity change, or the photochemical change of the terminal electrode by direct sunlight, the solderability and electrical performance may deteriorate. Do not store capacitors under direct sunlight or dewing condition. To store products on the shelf and avoid exposure to moisture.

▣ **Recommended soldering conditions**

The lead-free termination MLCCs are not only to be used on SMT against lead-free solder paste, but also suitable against lead-containing solder paste. If the optimized solder joint is requested, increasing soldering time, temperature and concentration of N<sub>2</sub> within oven are recommended.

